



ARENASHIELD

FOIL / FIBERGLASS-POLYESTER BLEND FABRIC

FACING COMPOSITION	DESCRIPTION	VALUES (ENGLISH)	VALUES (METRIC)
Foil	Aluminum	0.0003 inch	7.6 micron
Adhesive	Flame Resistant		
Fabric	Fiberglass/Polyester Blend	75 lbs / 3000 ft ²	122 g / m ²

PHYSICAL PROPERTIES	TEST METHOD	VALUES (ENGLISH)	VALUES (METRIC)
Basis Weight	Scale	40 lbs / 1000 ft ²	195 g / m ²
Permeance (WVTR)	ASTM E96 Procedure A	0.02 perm (grains/hrft ² in Hg)	1.15 ng / N's
Bursting Strength	ASTM D774	250 psi	17.6 kg / cm ²
Puncture Resistance	ASTM C1136	550 beach units	16.4 Joules
Tensile Strength	ASTM C1136	195 lbs/inch width(MD) 150 lbs/inch width(XD)	34.1 kN / m (MD) 26.3 kN / m (XD)
Caliper / Thickness	Micrometer	0.006 inch	152 micron
Accelerated Aging	30 Days @ 95% RH, 120°F (49°C)	No Corrosion No Delamination	No Corrosion No Delamination
Low Temperature Resistance	ASTM D1790 -40°F (-40°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
High Temperature Resistance	4 hours @ 240°F (116°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
Water Immersion	24 hours @ 73°F (23°C)	No Delamination	No Delamination
Mold Resistance	ASTM C665 / C1338	No Growth	No Growth
Dimensional Stability	ASTM D1204	0.25%	0.25%
Emissivity	ASTM E408	0.03	0.03

FIRE TESTING	ASTM E84 / UL 723		CAN ULC-S102M		 
	Foil Side	Fabric Side	Foil Side	Fabric Side	
Flame Spread	5	5	5	5	
Smoke Developed	5	5	5	5	

Physical Properties based upon statistical averages, Weight / Thickness +/- 10%

“LAMTEC” AND “WMP” ARE REGISTERED TRADEMARKS OF LAMTEC CORPORATION

5010 River Road Mount Bethel, Pennsylvania 18343-5610 U.S.A.
Phone: (570) 897-8200 Fax: (570) 897-6081 Web: www.lamtec.com