

ROXUL AFB®

Acoustical Fire Batt

Product Description & Application

ROXUL AFB® is a mineral wool batt insulation for interior partitions in commercial constructions where superior fire resistance and acoustical performance is required.

	Performance	Test Standard																																																						
Compliance	Mineral Fiber Thermal Insulation for Buildings, Type 1 Compliant Mineral Fiber Blanket Thermal Insulation, Type 1 Compliant Mineral Fiber Blanket Thermal Insulation, Type 7 Compliant MEA Approval, New York City Approval City of Los Angeles Approval	CAN/ULC S702 ASTM C665 ASTM C553 338-97-M RR 25444																																																						
Reaction to Fire	Flame spread index = 0 ; Smoke developed index = 0 Flame spread index = 0 ; Smoke developed index = 0 Determination of Non Combustibility of Building Materials - Non Combustible Behaviour of materials at 750°C - Non Combustible Smoulder Resistance - 0.09%	ASTM E84 (UL 723) CAN/ULC S102 CAN/ULC S114 ASTM E136 CAN/ULC S129																																																						
Density	Actual Density - 2.8 lbs/ft³ (45 kgs/m³)	ASTM C303																																																						
Corrosion Resistance	Stress Corrosion Cracking Tendency of Austenitic Stainless Steel - Passed Corrosion of Steel - Passed	ASTM C795 ASTM C665																																																						
Air Erosion	Maximum Air Velocity 1000 fpm (5.08 m/s)	UL 181																																																						
Thickness Dimensions	1" through 4" (25.4mm - 101.6mm) in 1/2" increments as well as 5" (127mm) and 6" (152.4mm) 16" x 48" (413mm x 1219mm), 24" x 48" (610mm x 1219mm)																																																							
Acoustical Performance	<table border="1"> <thead> <tr> <th>Thickness</th> <th>125 Hz</th> <th>250 Hz</th> <th>500 Hz</th> <th>1000 Hz</th> <th>2000Hz</th> <th>4000 Hz</th> <th>NRC</th> <th>ASTM C423</th> </tr> </thead> <tbody> <tr> <td>1.0"</td> <td>0.14</td> <td>0.25</td> <td>0.65</td> <td>0.9</td> <td>1.01</td> <td>1.01</td> <td>0.7</td> <td></td> </tr> <tr> <td>1.5"</td> <td>0.18</td> <td>0.44</td> <td>0.94</td> <td>1.04</td> <td>1.02</td> <td>1.03</td> <td>0.85</td> <td></td> </tr> <tr> <td>2"</td> <td>0.28</td> <td>0.6</td> <td>1.09</td> <td>1.09</td> <td>1.05</td> <td>1.07</td> <td>0.95</td> <td></td> </tr> <tr> <td>3"</td> <td>0.52</td> <td>0.96</td> <td>1.18</td> <td>1.07</td> <td>1.05</td> <td>1.05</td> <td>1.05</td> <td></td> </tr> <tr> <td>4"</td> <td>0.86</td> <td>1.11</td> <td>1.2</td> <td>1.07</td> <td>1.08</td> <td>1.07</td> <td>1.1</td> <td></td> </tr> </tbody> </table>	Thickness	125 Hz	250 Hz	500 Hz	1000 Hz	2000Hz	4000 Hz	NRC	ASTM C423	1.0"	0.14	0.25	0.65	0.9	1.01	1.01	0.7		1.5"	0.18	0.44	0.94	1.04	1.02	1.03	0.85		2"	0.28	0.6	1.09	1.09	1.05	1.07	0.95		3"	0.52	0.96	1.18	1.07	1.05	1.05	1.05		4"	0.86	1.11	1.2	1.07	1.08	1.07	1.1		
Thickness	125 Hz	250 Hz	500 Hz	1000 Hz	2000Hz	4000 Hz	NRC	ASTM C423																																																
1.0"	0.14	0.25	0.65	0.9	1.01	1.01	0.7																																																	
1.5"	0.18	0.44	0.94	1.04	1.02	1.03	0.85																																																	
2"	0.28	0.6	1.09	1.09	1.05	1.07	0.95																																																	
3"	0.52	0.96	1.18	1.07	1.05	1.05	1.05																																																	
4"	0.86	1.11	1.2	1.07	1.08	1.07	1.1																																																	
	Please contact ROXUL for STC ratings on tested wall assemblies	ASTM E90																																																						
Fire Rated Designs	ULC Classification Code: BZJZC UL Classification Code: BZJZ																																																							



Issued 04-01-16
 Supersedes 10-27-14

NOTE: *Mast Format 1995 Edition **Master Format 2004 Edition. As ROXUL Inc has no control over installation design and workmanship, accessory materials or application conditions, ROXUL Inc. does not warranty the performance or results of any installation containing ROXUL Inc's products. ROXUL Inc's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose.