



COMPLEMENTARY PRODUCTS

APPLICATIONS

ROOFING

WALLS

FOUNDATIONS

ELASTOCOL STICK H₂O

TECHNICAL DATA SHEET 160112SCANE

(supersedes 151118SCANE)

DESCRIPTION

ELASTOCOL STICK H₂O is a water-based polymer emulsion primer.

It is designed to improve the adhesion of self-adhesive waterproofing membrane on most substrates.

Particularly recommended when the use of solvent-based primer is not advised.

RECOMMENDED SUBSTRATES

Concrete, wood or polystyrene surfaces as well as on gypsum boards.

SURFACE PREPARATION

Surfaces must be dry, clean and free of oil, grease, debris or dirt.

APPLICATION

** Please read the restrictions before the application of the products.

ELASTOCOL STICK H₂O is applied using a paint brush or a roller.

Membranes must be installed on the same day as the application of ELASTOCOL STICK H₂O.

Apply the primer layer at a rate of 0.2 L/m² (0.5 US gal/100 ft²) with a thickness of 8 mil. Coverage rate may vary depending of the substrate.

Minimum temperature application: -4 °C (25 °F).

Drying time varies depending on temperature, relative humidity, wind and the surface.

RESTRICTIONS

Not suitable for plastic surfaces such as vinyl siding, metal surfaces or water repellent-treated panels.

Do not use to seal self-adhesive membrane joints, as a primer between two membranes or on asphaltic boards (SOPRABOARD).

FOR COMPLETE INFORMATION ON PRODUCT APPLICATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

PACKAGING

| Specifications | ELASTOCOL STICK H ₂ O |
|---------------------------------|---|
| Physical state | Liquid |
| Colour | Blue |
| Specific gravity at 20°C (68°F) | 1.03 kg/L |
| Container | 19 L (5 US gal) |
| Coverage rate per container | 95 m ² (1020 ft ²) |

(All values are nominal)



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS_ELASTOCOL_STICK_H2O.indd

ELASTOCOL STICK H₂O

TECHNICAL DATA SHEET 160112SCANE

(supersedes 151118SCANE)



COMPLEMENTARY PRODUCTS

APPLICATIONS

ROOFING

WALLS

FOUNDATIONS

PROPERTIES

| Properties | ELASTOCOL STICK H ₂ O |
|-------------------------------------|--|
| Solids by weight | 55% |
| Brookfield viscosity, 25 °C (77 °F) | 900 cP |
| Drying time | 30 minutes to 3 hours, depending on temperature and quantity applied |

(All values are nominal)

CLEANING

Tools and uncured adhesive can be cleaned with solvents, such as mineral spirits, Varsol, Xylene, etc.

STORAGE AND HANDLING

Storage: Up to 24 months in original sealed container, protected from moisture. Keep from freezing. Store in a ventilated place, away from heat and direct sunlight.

For more information, refer to instructions on the container label and relevant safety data sheet (SDS).



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS_ELASTOCOL_STICK_H2O.indd

2/2